

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



544571

(43) International Publication Date  
19 August 2004 (19.08.2004)

PCT

(10) International Publication Number  
**WO 2004/069920 A1**

(51) International Patent Classification<sup>7</sup>: **C08L 23/16**

MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(21) International Application Number:  
PCT/JP2003/001312

(22) International Filing Date: 7 February 2003 (07.02.2003)

(25) Filing Language: English

(26) Publication Language: English

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): DU PONT-MITSUI POLYCHEMICALS CO., LTD. [JP/JP]; 5-2, Higashi-Shimbashi 1-Chome, Minato-ku, Tokyo 105-7117 (JP).

**Declaration under Rule 4.17:**

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): NAKANO, Shigenori [JP/JP]; 402-2, Matsugashima, Ichihara-shi, Chiba 290-0035 (JP). MAKI, Nobuyuki [JP/JP]; 2-5, Yushudainishi, Ichihara-shi, Chiba 299-0125 (JP). ICHINOSEKI, Chikara [JP/JP]; 1-3-23, Yatsu, Narashino-shi, Chiba 275-0026 (JP).

(74) Agent: NAKAJIMA, Shigemitsu; Nichiyo Bldg. 3F, 11-12, Kanda Mitoshiro-cho, Chiyoda-ku, Tokyo 101-0053 (JP).

**Published:**

— with international search report

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: THERMOPLASTIC RESIN COMPOSITION, PROCESS FOR MANUFACTURE AND USE THEREOF

(57) Abstract: The present invention relates to a thermoplastic resin composition comprising (A) ionomer of ethylene/(meth)acrylic acid copolymer 60 to 96.7% by weight, (B) ethylene or alpha-olefin/glycidyl monomer copolymer 0.3 to 10% by weight and (C) propylene/alpha-olefin copolymer 3 to 30% by weight. The resin composition has excellent processability, workability, visual qualities, abrasion resistance, scratch resistance, surface hardness, stain resistance, heat resistance, etc, and is usable for building materials such as handrails, flooring materials and wall papers; car interior-exterior parts, toys, stationery, sundries, etc.

WO 2004/069920 A1